



Keeling & Walker

World Leader in Tin Oxide



Whieldon Road, Stoke-on-Trent, ST4 4JA, UK

Telephone: +44 (0) 1782 744136

Fax: +44 (0) 1782 744126

e.mail: sales@keelingwalker.co.uk

Website: www.keelingwalker.co.uk

HIGH SURFACE AREA TIN OXIDE (HSATO-S*)

DATA SHEET - 047 Issue 2, Effective Date: 23/04/2008

Synonyms: Silica doped tin oxide, silica doped stannic oxide

C.A.S. No: 18282-10-5

EINECS No: 2421590

Description: High surface area tin oxide is supplied as a white or pale yellow powder consisting of aggregates of spherical primary particles. Uses include catalysis and ion exchange.

TYPICAL PROPERTIES:

Physical characteristics

Surface area (BET):	> 100 m ² g ⁻¹
Specific gravity:	6.9
Tap Density:	2000 g l ⁻¹
Average particle size	< 5 microns

Chemical data (as oxides):

Pb, Sb	each typically <0.03%
Fe, Bi, Cu, As	each typically <0.02%
Co, Ni, Ag, Cd, Mg, Mn, Zn	each typically <0.001%
Total of impurities listed	0.15% maximum

All information is given in good faith but without warranty.
This Data Sheet supersedes and replaces all previous issues.

Keeling & Walker products are manufactured under the ISO 9001 Quality Management System and the ISO 14001 Environmental Management System